

EcoBoard GK1 machine-finished front

Chipboard with machine-finished front and light grey back, can be die-cut and grooved



GRAMMAGE	THICKNESS	BULK	BENDING STIFFNESS	
g/m^2	μm	cm^3/g	MD Nmm	CD Nmm
400	550	1.38	80	22
450	650	1.44	92	25
500	700	1.40	113	31
550	770	1.40	127	38
600	850	1.42	202	60
650	920	1.42	247	94
700	1040	1.49	282	122
750	1060	1.41	296	131
800	1200	1.50	337	150



APPLICATIONS

Sleeve boxes • folding cartons
• calendar backing • POS displays

PRINTING

Offset printing • screen printing

CONVERSION

Die cutting, creasing, grooving

ADDITIONAL INFORMATION

www.kapag.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±7%
Thickness (DIN EN 20534)	±7%
Bulk	±7%
Stiffness (DIN 53121)	-15%
Brightness (ISO 2470)	
Opacity (ISO 2471)	
Roughness (ISO 8791/4)	

Printing Surface Properties

ISO Brightness	
Roughness	
Opacity	

Aging Resistance (Archiving Standards)

ISO 9706	
ISO 16245 Type B	



The mark of
responsible forestry
FSC® C058892